

**Data sheet**



**URSA INDUSTRY**  
**Extruded polystyrene**  
**NIII L**

**Technical properties**

Property	Value							Unit	Norm
	30	40	50	60	70	80	100		
Thickness	30	40	50	60	70	80	100	mm	EN 823
Width	0,60	0,60	0,60	0,60	0,60	0,60	0,60	m	EN 822
Length	1,25	1,25	1,25	1,25	1,25	1,25	1,25	m	EN 822
Fire	E	E	E	E	E	E	E		EN 13501
Thermal conductivity (10 °C/90 days)	0,034	0,034	0,034	0,034	0,034	0,034	0,034	W/(m·K)	EN12667 / EN12939
Thermal resistance (RD)	0,90	1,20	1,50	1,80	1,95	2,20	2,80	W/(m·K)	EN 13164
Thickness tolerance	+2 / -2	+2 / -2	+2 / -2	+3 / -2	+3 / -2	+3 / -2	+3 / -2	mm	EB 823
Squareness (Sb)	5	5	5	5	5	5	5	mm//m	En 824
Flatness (S max)	7	7	7	7	7	7	7	m	EN 825
Dimensional Stability 23°C and 90%	≤5%	≤5%	≤5%	≤5%	≤5%	≤5%	≤5%	%	EN 1604
Deformation under compressive load and temperatura conditions	≤5%	≤5%	≤5%	≤5%	≤5%	≤5%	≤5%	70°/168h/40kPa	EN 1605
Tensile strength perpendicular to faces	>100	>100	>100	>100	>100	>100	>100	kPa	En 1607
Compressive stress	≥300	≥300	≥300	≥300	≥300	≥300	≥300	kPa	EN 826
Compressive creep	125	125	125	125	125	125	125	kPa	EN 12431
Long term wáter absorption by inmersión (Wp)	≤0,7	≤0,7	≤0,7	≤0,7	≤0,7	≤0,7	≤0,7	%	EN 12087
Long term wáter absorption by diffusion (Wd)	3	3	3	2,7	2,1	1,5	1,5	%	En 12088
Freeze-thaw resistance (10)	<10	<10	<10	<10	<10	<10	<10	%	EN 12088
Freeze-thaw resistance (WIt)	≤1	≤1	≤1	≤1	≤1	≤1	≤1	%	EN 12088
Lateral finish	half lap joint	half lap joint	half lap joint	half lap joint	half lap joint	half lap joint	half lap joint		

Designation Code:

Thickness ≥40 mm: T1-CS(10/Y)300-DLT(2)5-DS(TH)-WL(T)0,7-WD(V)3-FT2

Thickness ≥50 mm: T1-CS(10/Y)300-DLT(2)5-DS(TH)-WL(T)0,7-C(2/1,5/50)125-WD(V)3-FT2

AENOR Certification Number: 020/003053

The technical information contained in this document reflects our knowledge and actual experience.

If you require more information, please, contact with us.

Sutac.aislantes@uralita.com

www.ursa.es